

SPECIFICATIONS

MARCH 2011

DURATUF 130

APPLICATIONS: Industrial packaging
Food packaging
Very high tear resistance
Engineered uses
Temperature use to 180 F

DESCRIPTION: Single layer film
Two sided sealing
Clarity
Octene LLDPE
Metallocene catalyst
FDA approved

SPECIFICATIONS:

Property	Units		1.5 mil	2.5 mil	3.5 mil	4.5 mil
O2TR	cc/100 sq. in.-day-atm		450	260	180	140
WVTR	g/100 sq. in.-day-atm		0.95	0.56	0.38	0.29
Dart	grams		720	1020	1280	1550
Secant	Psia	MD	20000	21000	21000	20000
modulus	Psia	TD	24000	23000	23000	23000
Tensile	Psia	MD	6500	5400	6000	5400
(at break)	%		480	570	630	620
	Psia	TD	4700	5500	5800	5500
	%		610	650	670	670
Tear	grams	MD	300	700	1200	1650
	grams	TD	820	1460	2060	2360

AVAILABILITY: Bottom seal bags 9" - 110" wide, 20" - 275" deep
Side seal bags 20" - 275" wide, 10" - 110" deep
Tubing 9" - 120" wide.
Single wound sheeting 10" - 120" wide.
Center fold sheeting 10" - 120" wide.
Thickness range 1.0 to 8.0 mils
Color natural

The information contained herein is based upon data believed to be reliable and relates only to the matters specifically contained herein. Although such information is, to the best of our knowledge and belief, accurate and reliable as of the date hereof, no representation, warranty (express or implied, or merchantability, fitness or otherwise) or guarantee is made as to the suitability, accuracy, reliability or completeness of the information. It is the user's responsibility to satisfy itself as to the suitability, accuracy, reliability and completeness of such information for its particular use. There is no warranty against patent infringement and General Films not be liable for any loss, damage, or injury that may occur from the use of this information. No statement herein shall be construed as an endorsement of any product or process.

**General
Films, Inc.**

INNOVATIONS IN PACKAGING

645 SOUTH HIGH STREET
COVINGTON, OHIO 45318
P: 937.473.2051
F: 937.473.2403
W: WWW.GENERALFILMS.COM