

SPECIFICATIONS

SEPTEMBER 2018

VF-2

APPLICATIONS: Vertical form fill and seal packaging
Temperature use to 180° F

DESCRIPTION: Coextruded film
Two sided sealing
Superior tensile strength
High dart impact
FDA approved
Metallocene catalyst skin layers for improved hot tack and low heat seal initiation temperature

SPECIFICATIONS:

Property	Units		1.5 mil	3.5 mil	5.5 mil
O2TR	cc/100 sq. in.-day-atm		325	125	75
WVTR	g/100 sq. in.-day-atm		0.66	0.27	0.18
Dart	grams		800	1300	2000
Secant modulus	Psia	MD	23000	26000	27000
	Psia	TD	25000	26000	27000
Tensile (at break)	Psia	MD	7200	7300	6700
	%		600	690	700
	Psia	TD	7500	7300	7300
	%		700	710	740
Tear	grams	MD	630	1430	2580
	grams	TD	820	1810	2820

AVAILABILITY: Thickness range 1.5 to 5.5 mils
Color Natural / White

The information contained herein is based upon data believed to be reliable and relates only to the matters specifically contained herein. Although such information is, to the best of our knowledge and belief, accurate and reliable as of the date hereof, no representation, warranty (express or implied, or merchantability, fitness or otherwise), or guarantee is made as to the suitability, accuracy, reliability or completeness of the information. It is the user's responsibility to satisfy itself as to the suitability, accuracy, reliability and completeness of such information for its particular use. There is no warranty against patent infringement and General Films not be liable for any loss, damage, or injury that may occur from the use of this information. No statement herein shall be construed as an endorsement of any product or process.

**General
Films, Inc.**

INNOVATIONS IN PACKAGING

645 SOUTH HIGH STREET
COVINGTON, OHIO 45318
P: 937.473.2051
F: 937.473.2403
W: WWW.GENERALFILMS.COM