

LB-725

APPLICATIONS: Vertical form/fill/seal machines
Horizontal form/fill/seal machines
Moisture barrier packaging
Temperature use to 180° F

DESCRIPTION: Coextruded film with HDPE barrier
One sided sealing
VLDPE Metallocene sealant layer
High density polyethylene exterior ply
FDA approved

SPECIFICATIONS:

Property	Units		1.2 mil	1.5 mil	1.8 mil
O2TR	cc/100 sq. in.-day-atm		140	115	95
WVTR	g/100 sq. in.-day-atm		0.29	0.25	0.22
Dart	grams		55	60	75
Secant modulus	Psia	MD	65000	73000	73000
	Psia	TD	93000	102000	96000
Tensile (at break)	Psia	MD	5500	6000	6000
	%		570	610	630
	Psia	TD	3700	3600	3500
	%		620	620	620
Tear	grams	MD	50	60	70
	grams	TD	610	750	780

AVAILABILITY: Bottom seal bags n/a
Side seal bags n/a
Tubing 30" - 60" wide.
Single wound sheeting 10" - 60" wide.
Center fold sheeting 15" - 60" wide.
Thickness range 1.2 to 3.0 mils
Color natural or tinted

The information contained herein is based upon data believed to be reliable and relates only to the matters specifically contained herein. Although such information is, to the best of our knowledge and belief, accurate and reliable as of the date hereof, no representation, warranty (express or implied, or merchantability, fitness or otherwise) or guarantee is made as to the suitability, accuracy, reliability or completeness of the information. It is the user's responsibility to satisfy itself as to the suitability, accuracy, reliability and completeness of such information for its particular use. There is no warranty against patent infringement and General Films not be liable for any loss, damage, or injury that may occur from the use of this information. No statement herein shall be construed as an endorsement of any product or process.