

SPECIFICATIONS

OCTOBER 2011

H2/BL

APPLICATIONS: Gas, aroma, flavor barrier
Vertical form/fill/seal machines
Bag printing and converting
Gas flush/MAP packaging
Temperature use to 180 F

DESCRIPTION: Coextruded film with EVOH barrier
Two sided sealing
VLDPE Metallocene sealant layers
Nylon interior ply
FDA approved

SPECIFICATIONS:

Property	Units		2.5 mil	3.5 mil	4.5 mil
O2TR	cc/100 sq. in.-day-atm		0.12	0.08	0.05
WVTR	g/100 sq. in.-day-atm		0.6	0.4	0.3
Dart	grams		650	1000	1100
Secant	Psia	MD	60000	64000	67000
modulus	Psia	TD	63000	63000	64000
Tensile	Psia	MD	6000	5900	6100
(at	%		370	380	390
Break)	Psia	TD	5500	5800	5500
	%		390	400	380
Tear	grams	MD	120	200	300
	grams	TD	180	240	290

AVAILABILITY: Bottom seal bags 38" - 66" wide, 20" - 100" deep.
Side seal bags 12" - 100" wide, 20" - 66" deep.
Tubing 38" - 74" wide.
Single wound sheeting 10" - 72" wide.
Center fold sheeting 20" - 74" wide.
Thickness range 2-1/2, 3-1/2, 4-1/2 mils
Color Natural or tinted blue

The information contained herein is based upon data believed to be reliable and relates only to the matters specifically contained herein. Although such information is, to the best of our knowledge and belief, accurate and reliable as of the date hereof, no representation, warranty (express or implied, or merchantability, fitness or otherwise), or guarantee is made as to the suitability, accuracy, reliability or completeness of the information. It is the user's responsibility to satisfy itself as to the suitability, accuracy, reliability and completeness of such information for its particular use. There is no warranty against patent infringement and General Films not be liable for any loss, damage, or injury that may occur from the use of this information. No statement herein shall be construed as an endorsement of any product or process.

**General
Films, Inc.**

INNOVATIONS IN PACKAGING

645 SOUTH HIGH STREET
COVINGTON, OHIO 45318

P: 937.473.2051

F: 937.473.2403

W: WWW.GENERALFILMS.COM