

SPECIFICATIONS

MARCH 2011

DURATUF 120

APPLICATIONS: Industrial packaging
Food packaging
Downgauging
High impact
Temperature use to 180 F

DESCRIPTION: Single layer film
Two sided sealing
Hexene LLDPE
Metallocene catalyst
FDA approved

SPECIFICATIONS:

Property	Units		1.5 mil	2.5 mil	3.5 mil	4.5 mil
O2TR	cc/100 sq. in.-day-atm		360	200	140	90
WVTR	g/100 sq. in.-day-atm		0.75	0.46	0.31	0.22
Dart	grams		380	780	1040	1450
Secant modulus	Psia	MD	29000	30000	31000	32000
	Psia	TD	29000	34000	34000	33000
Tensile (at break)	Psia	MD	5100	5700	6200	6100
	%		490	580	640	660
	Psia	TD	4700	5500	6200	6200
	%		480	610	660	680
Tear	grams	MD	240	610	990	1350
	grams	TD	750	1110	1870	2310

AVAILABILITY: Bottom seal bags 9" - 110" wide, 20" - 275" deep
Side seal bags 20" - 275" wide, 10" - 110" deep
Tubing 9" - 120" wide.
Single wound sheeting 10" - 120" wide.
Center fold sheeting 10" - 120" wide.
Thickness range 1.0 to 8.0 mils
Color natural

The information contained herein is based upon data believed to be reliable and relates only to the matters specifically contained herein. Although such information is, to the best of our knowledge and belief, accurate and reliable as of the date hereof, no representation, warranty (express or implied, or merchantability, fitness or otherwise), or guarantee is made as to the suitability, accuracy, reliability or completeness of the information. It is the user's responsibility to satisfy itself as to the suitability, accuracy, reliability and completeness of such information for its particular use. There is no warranty against patent infringement and General Films not be liable for any loss, damage, or injury that may occur from the use of this information. No statement herein shall be construed as an endorsement of any product or process.

**General
Films, Inc.**

INNOVATIONS IN PACKAGING

645 SOUTH HIGH STREET
COVINGTON, OHIO 45318
P: 937.473.2051
F: 937.473.2403
W: WWW.GENERALFILMS.COM