

SPECIFICATIONS

MARCH 2012

PR-2/175

APPLICATIONS: Precut produce packaging
Vertical form/fill/seal machines
Bag printing and converting
Temperature use to 180 F

DESCRIPTION: Coextruded film
Two sided sealing
Metallocene sealant layers
Enhanced stiffness
FDA approved

SPECIFICATIONS:

Property	Units		2.0 mil	3.0 mil
O2TR	cc/100 sq. in.-day-atm		175	117
WVTR	g/100 sq. in.-day-atm		0.4	0.3
Dart	grams		240	370
Secant	Psia	MD	43000	46000
modulus	Psia	TD	51000	49000
Tensile	Psia	MD	7200	6700
(at	%		620	670
Break)	Psia	TD	5600	6000
	%		690	730
Tear	grams	MD	340	560
	grams	TD	1050	1230

AVAILABILITY: Single wound sheeting 15" - 58" wide.
Center fold sheeting 15" - 58" wide.
Thickness range 2.0 - 4.0 mils
Color natural or tinted blue

The information contained herein is based upon data believed to be reliable and relates only to the matters specifically contained herein. Although such information is, to the best of our knowledge and belief, accurate and reliable as of the date hereof, no representation, warranty (express or implied, or merchantability, fitness or otherwise) or guarantee is made as to the suitability, accuracy, reliability or completeness of the information. It is the user's responsibility to satisfy itself as to the suitability, accuracy, reliability and completeness of such information for its particular use. There is no warranty against patent infringement and General Films not be liable for any loss, damage, or injury that may occur from the use of this information. No statement herein shall be construed as an endorsement of any product or process.

**General
Films, Inc.**

INNOVATIONS IN PACKAGING

645 SOUTH HIGH STREET
COVINGTON, OHIO 45318

P: 937.473.2051

F: 937.473.2403

W: WWW.GENERALFILMS.COM