

SPECIFICATIONS

JANUARY 2016

LB-730

APPLICATIONS: Precut produce packaging
Premade bags
Vertical form/fill/seal machines
Temperature use to 180 F

DESCRIPTION: Coextruded film
Two sided sealing
Metallocene sealant layers
FDA approved

SPECIFICATIONS:

Property	Units		2.0 mil	3.25 mil
O2TR	cc/100 sq. in.-day-atm		160	110
WVTR	g/100 sq. in.-day-atm		0.4	0.3
Dart	grams		260	390
Secant modulus	Psia	MD	48000	41000
	Psia	TD	66000	61000
Tensile	Psia	MD	4900	5300
(at Break)	%		650	750
	Psia	TD	5200	5100
	%		820	860
Tear	grams	MD	310	680
	grams	TD	1100	1600

AVAILABILITY: Bottom seal bags 30" - 60" wide, 20" - 100" deep
Side seal bags 10" - 200" wide, 15" - 60" deep
Tubing 30" - 60" wide
Single wound sheeting 10" - 60" wide
Center fold sheeting 15" - 60" wide
Thickness Range 0.0015" - 0.008"
Color natural or tinted blue

The information contained herein is based upon data believed to be reliable and relates only to the matters specifically contained herein. Although such information is, to the best of our knowledge and belief, accurate and reliable as of the date hereof, no representation, warranty (express or implied, or merchantability, fitness or otherwise), or guarantee is made as to the suitability, accuracy, reliability or completeness of the information. It is the user's responsibility to satisfy itself as to the suitability, accuracy, reliability and completeness of such information for its particular use. There is no warranty against patent infringement and General Films not be liable for any loss, damage, or injury that may occur from the use of this information. No statement herein shall be construed as an endorsement of any product or process.

**General
Films, Inc.**

INNOVATIONS IN PACKAGING

645 SOUTH HIGH STREET
COVINGTON, OHIO 45318
P: 937.473.2051
F: 937.473.2403
W: WWW.GENERALFILMS.COM