

# SPECIFICATIONS

MARCH 2011

## DURATUF 75

**APPLICATIONS:** Industrial packaging  
General purpose polyethylene  
Non critical uses  
Temperature use to 180 F

**DESCRIPTION:** Single layer film  
Two sided sealing  
Wide spec LLDPE  
Low cost

**SPECIFICATIONS:**

Property	Units		1.5 mil	2.5 mil	3.5 mil	4.5 mil
Dart	grams		65	140	200	320
Secant modulus	Psia	MD	25000	26000	27000	28000
	Psia	TD	33000	31000	32000	32000
Tensile (at break)	Psia	MD	3000	3000	3000	3000
	%		600	600	600	600
	Psia	TD	2500	2500	2500	2500
	%		600	600	600	600
Tear	grams	MD	50	160	340	580
	grams	TD	350	620	780	990

**AVAILABILITY:** Bottom seal bags 9" - 110" wide, 20" - 275" deep  
Side seal bags 20" - 275" wide, 10" - 110" deep  
Tubing 9" - 120" wide.  
Single wound sheeting 10" - 120" wide.  
Center fold sheeting 10" - 120" wide.  
Thickness range 1.25 to 6.0 mils  
Color natural, black

The information contained herein is based upon data believed to be reliable and relates only to the matters specifically contained herein. Although such information is, to the best of our knowledge and belief, accurate and reliable as of the date hereof, no representation, warranty (express or implied, or merchantability, fitness or otherwise), or guarantee is made as to the suitability, accuracy, reliability or completeness of the information. It is the user's responsibility to satisfy itself as to the suitability, accuracy, reliability and completeness of such information for its particular use. There is no warranty against patent infringement and General Films not be liable for any loss, damage, or injury that may occur from the use of this information. No statement herein shall be construed as an endorsement of any product or process.

**General  
Films, Inc.**

INNOVATIONS IN PACKAGING

645 SOUTH HIGH STREET  
COVINGTON, OHIO 45318  
P: 937.473.2051  
F: 937.473.2403  
W: WWW.GENERALFILMS.COM